




# Doodle

240, price group 3


Soft and plushy like a fluffy cloud, Doodle fabric creates the perfect cozy atmosphere for any interior. Ideal for those who follow the latest trends but also appreciate the comfort and safety of late-night evenings with a good book.



100% Polyester



Martindale: > 100.000



Lightfastness: 5


## PRODUCT CHARACTERISTICS

Product group	knitwear
Applications	sofa's, chairs with fitted and loose fitting upholstery
Composition faceside	100% PES
Composition upside	100% PES
Bonding	n/a
Statistic code	60011000
Dyeing method	piece dyed
Available colours	3



LIFESTYLE  
FURNITURE  
SINCE 1978






## DURABILITY SPECIFICATIONS

Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.00		min. 20.000	min. 40.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	n/a		min. 3-4	min. 4	n/a
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min. 5	B
	middle colours	CTL	grade	5		min. 4	min. 5	B
	dark colours	CTL	grade	5		min. 4	min. 5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette.	CTL		passed				

## PROCESSING SPECIFICATION

Minimum workable width in centimeters	± 143							
Roll length in meters	± 20							
Material weight in grams per linear meter	± 1020							
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	612	640	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	104,6	92,5	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,2	2,2	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	13,8	15,3	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				

All information is based on the data provided by the manufacturer.

CLEANING SPECIFICATIONS								
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30° C DIN EN	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	0,0	n/a	n/a	A/A
    				<ul style="list-style-type: none"> <li>- It is essential to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.</li> <li>- Please note that during washing the damp and dirt prevented treatment will disappear faster.</li> <li>- Dirt and damp prevention treatment applied.</li> </ul>				