




Earth

384, price group 2


This piece of dyed knitted velvet is strong and machine washable at 30° C. It's a sustainable textile that is part of a www.wovenbottles.com collection. The pile provides a comfortable softness and creates a light shiny elegant look. Velvet is made sustainably from 100% RPET bottles. This luxurious upholstery fabric is durable and very easy to clean and maintain. Earth is suitable for all types of upholstery, and is available in a wide range of trendy, modern, and commercial colors.



100% recycled PET



Martindale: >100.000



Lightfastness: 5

PRODUCT CHARACTERISTICS

Product group	knitted velvet
Applications	sofa's, chairs with fitted and loose fitting upholstery
Composition faceside	100% RPET
Composition backside	n/a
Bonding	n/a
Statistic code	60053900
Dyeing method	piece dyed
Available colours	17



LIFESTYLE
FURNITURE
SINCE 1978


DURABILITY SPECIFICATIONS

Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 20.000	min. 40.000	A
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11, Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min. 5	B
	middle colours	CTL	grade	5		min. 4	min. 5	B
	dark colours	CTL	grade	5		min. 4	min. 5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/B
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324, Schedule 4 part 1 Ignition source 0: cigarette.	CTL		passed				

PROCESSING SPECIFICATION

Minimum workable width [cm]	± 138							
Roll length [m]	± 35							
Material weight [g/m]	± 620							
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	631	982	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	46,7	60,7	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180 N	CTL	mm	2,1	2,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel	passed					

All information is based on the data provided by the manufacturer.

CLEANING SPECIFICATIONS								
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30° C DIN EN	DIN EN ISO 5077:2008-04. DIN EN ISO 6330:2013-02. DIN EN ISO 3759:2011-08	CTL	%	0,0	0,0	n/a	n/a	A/A
				<p>- It is essential to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.</p>				