




Society

433, price group 3


This sustainable bouclé textile has a luxurious look & feel. Made from 100% recycled polypropylene, Society is multicoloured, soft with a rough and modern look. Society fits all types of upholstery, so it can be applied widely, as loose covers as well as on tight-fitted furniture. It is voluminous and has a comfortable hand-feel.



100% Recycled
Polipropylen



Martindale: 45.000




Lightfastness: 5

PRODUCT CHARACTERISTICS

Product group	flatweave
Applications	sofa's, chairs with fitted and loose fitting upholstery
Composition faceside	100% RPP
Composition upside	n/a
Bonding	n/a
Statistic code	54077300
Dyeing method	yarn dyed
Available colours	17


DURABILITY SPECIFICATIONS

Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	45.000		min. 12.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min. 5	B
	middle colours	CTL	grade	5		min. 4	min. 5	B
	dark colours	CTL	grade	5		min. 4	min. 5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette.	CTL		passed				

PROCESSING SPECIFICATION

Minimum workable width in centimeters	± 138							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 588							
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	903	1,375	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	148,0	140,4	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,2	2,2	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	56,5	41,9	n/a	n/a	n/a
Chemical	REACH	Centexbel		passed				

All information is based on the data provided by the manufacturer.

CLEANING SPECIFICATIONS								
Test	Test specification	Executed by laboratory:	Unit	Test result		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30° C DIN EN	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0.0	0.0	n/a	n/a	A/A
				<ul style="list-style-type: none"> - It is essential to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing. - Please note that during washing the damp and dirt prevented treatment will disappear faster. - Dirt and damp prevention treatment applied. 				